




Processing Guides for WONDERLITE® PC-122

- A Pre-drying 120°C x 4 hrs
 depending on
- a) Humidity
 - b) Storage conditions
 - c) Dryer's performance

B. Barrel Setting Profile



Grade / Application		Nozzle	Compression zone	Feeding zone	Mold Temperature *
PC-122	max.(°C)	300	310	300	70 -120
	min.(°C)	240	240	220	

- * varying with
- a) Thickness of molded articles
 - b) Cooling system design
 - c) Gate and runner system

NOTE :

1. Keep the resin from dust and contamination during handling and production.
2. Do not retain the hot melt at the barrel for a long time between injection cycles.
3. Temperature setting of manifold system should not exceed 330°C to avoid melt from degrading.
4. The injection temperature corresponds to your mould design and piece thickness.

For further information, please contact your local agent or fax to CHIMEI-ASAHI Technical Services Dept. at 886-6-2667983/2667984