

Combining the Advantages of Thermoplastic Processing and Superior Elastomeric Performance

Sarlink[®] 4100 series grades exemplify our curiosity and discipline in research, and our care and dedication in production. Our engineers have succeeded in creating a product range that feels like rubber yet processes easily like plastic. Sarlink[®] 4100 is based on carefully selected raw materials in combination with a proprietary process technology, which combines superb elastic properties with the processing ease of thermoplastics.

High Raw-Material Efficiency

Sarlink[®] is an environmentally friendly equivalent to general purpose thermoset rubber compounds, with high chemical resistance comparable to general purpose polychloroprene rubber. This unique combination enables a broad range of applications. Compared to thermoset rubber, using Sarlink[®] will reduce production costs due to its shorter cycle times, reduced energy needs, and a very high raw-material efficiency as a result of its recyclability.

Main Characteristics

The compounds of the Sarlink[®] 4100 series combine chemical and abrasion resistance with high tensile properties and excellent elastic properties such as low tension and compression sets. They outperform the Sarlink[®] 3100 series in many respects. Our compounds can be processed using standard

thermoplastic processing techniques such as injection molding, extrusion and blow molding. The Sarlink[®] 4100 series contains a wide variety of grades with hardnesses from 45 Shore A up to 50 Shore D, in black and natural colors.

Safety

Sarlink[®] does not present a toxic hazard through skin contact or inhalation when handled under normal conditions. Contact with molten polymers or inhalation of fumes should be avoided during processing. More and detailed information can be downloaded from www.teknorapex.com/sarlink.

Other Teknor Apex TPE products

Sarlink[®] is one of six product families within the Teknor Apex TPE portfolio. The Sarlink[®] range itself contains multiple grade series, each with a specialty set of properties designed to fit a variety of application requirements. In addition to standard Sarlink[®] series, special Sarlink[®] grades exist or can be developed to meet unique customer requirements, such as specific OEM or regulatory approval requirements, UV resistance, or potable water contact. Information regarding these specialty grades and other Sarlink[®] series are available via your representative or at www.teknorapex.com/sarlink.

Data Sarlink® 4100 general purpose grades (ISO standards - typical properties)

Typical properties	Test standard	Units S.I.	4145	4155	4165	4175	4180	4190	4139D	4149D
Density	ISO 1183	kg/m ³	960	960	960	960	960	950	950	940
Hardness (5 sec delay)	ISO 868	Shore A or D								
Extruded sample			45A	53A	63A	72A	79A	86A	39D	47D
Injection molded sample			48A	56A	65A	75A	83A	90A	40D	51D
Tensile properties	ISO 37									
<i>Flow direction</i>										
Tensile strength at break		MPa	3,1	4,3	5,8	7,2	9,0	13,6	18,0	21,6
Modulus at 100% elongation		MPa	2,6	3,1	4,2	5,3	6,8	10,2	13,3	18,0
Elongation at break		%	180	240	280	300	330	380	420	420
<i>Cross flow direction</i>										
Tensile strength at break		MPa	4,3	5,2	6,8	8,5	10,2	14,5	19,0	23,1
Modulus at 100% elongation		MPa	1,3	2,0	2,5	3,3	4,5	6,7	8,9	13,0
Elongation at break		%	550	550	570	590	620	650	700	740
Tear strength (cross flow)	ISO 34B									
Unnicked angle		kN/m	20	22	29	39	48	71	97	141
Compression set	ISO 815									
22 hrs @23°C		%	11	14	17	22	26	36	46	55
22 hrs @70°C		%	26	26	27	31	40	48	56	64
70 hrs @125°C		%	35	37	40	45	58	72	80	85
Hot air aging (cross flow direction)	ISO 188									
<i>168 hrs @150°C</i>										
Change in hardness		pts	0	2	2	3	2	3	2	2
Retention tensile strength at break		%	95	91	89	91	90	92	85	85
Retention modulus at 100% elongation		%	97	98	100	103	105	110	115	115
Retention elongation at break		%	106	94	89	84	85	83	80	80
<i>1000 hrs @135°C</i>										
Change in hardness		pts	2	2	2	2	3	3	2	2
Retention tensile strength at break		%	98	95	91	98	91	89	85	92
Retention modulus at 100% elongation		%	100	102	104	105	110	115	120	125
Retention elongation at break		%	113	101	92	95	85	84	80	80
Volume swell	ISO 1817									
70 hrs @125°C in IRM 903 oil		%	112	85	83	78	64	54	47	38
Apparent shear viscosity	ISO 11443									
@206 1/s, 200°C	Capillary	Pa.s	320	320	340	340	340	340	370	440

Some grades may not be available locally
Revised: August 1, 2008

sarlink®

TA TEKNOR APEX

Corporate Headquarters

Telephone +1.866.438.8737 (all TPE enquiries)
Telephone +1.800.556.3864 or
+1.401.725.8000 (Teknor Apex Company)

Europe

Telephone: +31.46.70.20.950

Singapore

Telephone: +65.6265.2544

China

Telephone: +86.512.6287.1550

Japan

Telephone: +81.352095151

About Teknor Apex TPE

The Thermoplastic Elastomer Division of Teknor Apex Company (TA TPE) is the most diversified manufacturer of TPEs, offering seven broad product families based on generically distinct chemistries and operating plants in the US, Europe, and Asia. The processes used by TA TPE produce compounds that exhibit outstanding rubber-like properties with particular characteristics while being processable at high rates like any other thermoplastic, as well as being recyclable. Visit www.teknorapex.com/tpe to see the TPE product families.

Headquartered in Pawtucket, Rhode Island, US, the Division is an international supplier to the appliance, automotive, construction, medical-device, wire and cable, and other consumer and industrial product industries. Other plastics businesses of Teknor Apex include the Bioplastics, Nylon, Specialty Compounding, and Vinyl Divisions and Teknor Color Company. Visit www.teknorapex.com.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of TA TPE, including product names, shall not be used or tested in any medical or food contact application without the prior written acknowledgement of TA TPE as to the intended use. Please note that some products may not be available in one or more countries.

info@teknorapex.com
www.teknorapex.com/sarlink