

TECHNICAL DATA SHEET

Revision Date: 2022.12.15

Version: 2.0

Product Name: Trifilon Revo1035

Trifilon Revo®1035

Art nr: Revo1035-10523-1

Natural Fiber Reinforced Polypropylene

Product Description

Trifilon Revo1035 is a natural fiber reinforced biocomposite engineered for injection moulding using recycled polypropylene from post-industrial processes. This biocomposite is a sustainable replacement for conventional polypropylene compounds.

Status: Commercially available

Typical Applications: Consumer Products, Home appliances, Office Supplies

Processing Method: Injection Molding

Attributes: Good Impact Resistance, Recycled, Biocomposite, Hemp

| Physical properties | Values | Units | Method |
|------------------------|--------|---------|-----------|
| Density | 1,02 | g/cm3 | ISO 1183 |
| Melt flow index, MFI | 8 | g/10min | ISO 1133 |
| MFI temperature | 230 | °C | |
| MFI Load | 2,16 | kg | |
| Shrinkage, with flow | 1,3 | % | ISO 294-4 |
| Shrinkage, across flow | 1,4 | % | |

| Mechanical properties | Values | Units | Method |
|-------------------------------------------|--------|-------|-------------|
| Tensile Modulus | 990 | MPa | ISO 527-2 |
| Tensile Stress at Yield | 19 | MPa | |
| Tensile Strain at Yield | 15 | % | |
| Tensile Stress at Break | 18 | MPa | |
| Tensile Strain at Break | 27 | % | |
| Charpy Impact Strength Notched (20°C) | 5,2 | kJ/m² | ISO 179/1eU |
| Charpy Impact Strength Unnotched (20°C) | 62,4 | kJ/m² | |
| Charpy Impact Strength Unnotched (-20°C)* | 20,3 | kJ/m² | |

^{*} modified procedure acc. to ISO 179/1eU

Legal notice

The above listed figures should be regarded as informational guide values only. Under certain conditions the material properties can be influenced to a significant degree by the processing methods and conditions. Neither Trifilon nor its distribution partners are responsible or liable for the accuracy of the information provided above. Neither shall Trifilon nor its distribution partners be responsible for the use of this information or any product, method or processing equipment described in this document. Any material properties and characteristics of products supplied by Trifilon, including technical advice on applications whether verbally, in writing or by testing the product, is given to the best of our knowledge. It does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended. The buyer is solely responsible for the application, utilization and processing of the product, and must observe the laws and government regulations and the consequential rights of third parties. Trifilon expressly advises against the use of this product in any medical, pharmaceutical or diagnostic application. At all times our Conditions of Sale apply. The brands "Trifilon" are registered trademarks of Trifilon AB, according to the international 'Nice-Classifications' (NCL9), 01, 09, 12.

Trifilon AB | Flättnaleden 6 | 611 45 Nyköping | Sweden Contact: info@trifilon.com